



广东梅州磁性材料有限公司

Guangdong Meizhou magnetic materials Co., Ltd.

Tel:+86-0753-2233758, 2233419

Fax:+86-0753-2233224, 6127801

粘结铁氧体料粉

主要技术指标 Main Technical Data

| 类别 Item | 牌号 Type | 主要磁特性 MAGNETIC Characteristic | | | | 磁粉含水率 Water content (%) | 平均粒度 Average Size (μm) | 用途 usage |
|------------|----------------------|-------------------------------------|----------------------------------|------------------------------------|--|----------------------------------|--|-------------|
| | | 剩磁 Br (mT) | 矫顽力 H _{CB} (kA/m) | 内禀矫顽力 H _{CJ} (kA/m) | 最大磁能积 (BH) _{MAX} (KJ/m ³) | | | |
| 粘结同性 钡料 | PO ₂ -B7 | 186 ± 10 | 103 ± 5 | 143 ± 10 | 5.8 ± 0.5 | ≤ 0.3 | 2.2-2.5 | 粘结同性橡胶磁 |
| | PO ₂ -B8 | 196 ± 10 | 110 ± 5 | 138 ± 10 | 7.6 ± 0.5 | ≤ 0.3 | 2.2-2.5 | |
| | PO ₂ -B9 | 214 ± 10 | 115 ± 5 | 135 ± 10 | 8.6 ± 0.5 | ≤ 0.3 | 1.5-2.2 | |
| 粘结同性 锶料 | PO ₂ -S8 | 214 ± 10 | 111 ± 5 | 133 ± 10 | 7.6 ± 0.3 | ≤ 0.3 | 2.4-3.0 | 粘结同性橡胶磁 |
| | PO ₂ -S10 | 223 ± 10 | 115 ± 5 | 126 ± 10 | 8.6 ± 0.3 | ≤ 0.3 | 2.2-2.8 | |
| | PO ₂ -S11 | 231 ± 10 | 115 ± 5 | 127 ± 10 | 9.5 ± 0.5 | ≤ 0.3 | 2.0-2.6 | |
| 粘结异性 | PO ₉ -S13 | ≥ 231 | ≥ 160 | ≥ 193 | ≥ 11.0 | ≤ 0.3 | 1.0-1.5 | 粘结异性橡胶磁 |